


# PROMAPAINT®-SC3 Reactive fire protective coating



www.promat-see.com







Technical data and properties	
Colour	white
Consistency	liquid
Density	1.350 kg/m³ ± 200 kg/m³
Solid content	71% ± 3 %
Expansion ratio	~ 1:15
Viscosity	~30 Pas at 20°C
Consumption	~1,85 kg/m² [1 mm DFT*]
Curing time between layers (for the same product)	~1000 µm after 8 hours (20°C, 50% RH)
Working temperature	+10°C up to +35°C
Storage temperature	+5°C up to +45°C
VOC-content	< 4 %
Dilution	water - max. 5%
Use category (according to ETAG 018-2)	without topcoat: type $Z_2$ with suitable protective topcoat: type X, Y and $Z_1$

<sup>\*</sup> Dry film thickness

#### **General description**

PROMAPAINT®-SC3 is a water borne intumescent paint for fire protection of steel and concrete structures.

#### Fields of application

- inside of buildings
- in open halls
- protective coating intended for all conditions (internal, semiexposed and exposed): according to ETAG 018-2

#### System advantages / customer benefits

- aesthetic surface (thin and seamless result)
- easy to apply
- can be repainted
- both open and hollow steel sections
- suitable for galvanized steel structures
- improving fire resistance of loadbearing brick and reinforced concrete members
- fire resistance up to R(EI) 180

# **Test certificate / approval**

PROMAPAINT®-SC3 is approved by ETA and is tested for steel structures and concrete components according to European standards. The coated steel or concrete components achieve fire resistance classes from R(EI) 15 to R(EI) 180.

#### **Processing**

PROMAPAINT®-SC3 may only be applied by trained professionals. Not for use in components that are constantly in highly humid areas or are exposed to aggressive gases. Surface must be free from grease, oil, rust, dirt or any other contaminant that may inhibit the bonding of PROMAPAINT®-SC3 to the primer. Stir well before use. Apply PROMAPAINT®-SC3 with a roller, brush or airless spray. Maximum dry film thickness (DFT) of one applied layer should be approximately 700  $\mu m$ , which is approximately 1.020  $\mu m$  of wet film thickness (WFT). When using a roller or brush, the maximum DFT of one applied layer should be approximately 350  $\mu m$  (approx. 510  $\mu m$  WFT). The processing temperature must be between +10°C and +35°C.

## Labelling

The product labeling complies with the current legal regulations.

# **Packaging**

- 25 kg sheet metal containers
- 900 kg per pallet

Subject to change.

## **Storage requirements**

Store in a cool, dry place. Shelf-life at least 18 months in original sealed containers.

# **Safety instructions**

PROMAPAINT®-SC3 is a technical paint, no mixing with conventional paints is allowed. Individual layers should be applied with care. Check compliance with the required layer thickness. Only tested and approved primers and topcoats should be used. Product details available on request at Promat.



## Slovenia, SEE Management

Promat d.o.o.

Kidričeva 56b 4220 Škofia Loka

T + 386 4 51 51 451

F + 385 4 51 51 450

E info@promat-see.com

www.promat-see.com

#### Romania

Branch office of Promat d.o.o. Slovenia

Str. Vulturilor Nr. 98, 5th Floor

030857 Bucharest

T +40 31 224 01 00

F +40 31 224 01 01

E info.ro@promat-see.com

www.promat-see.com

# **Bulgaria**

Branch office of Promat d.o.o. Slovenia

Aleksandar Zhendov 6 1113 Sofia

M +359 888 14 38 85

M +359 878 81 51 05

E info.bg@promat-see.com

www.promat-see.com

# Serbia, Macedonia, Montenegro,

Branch office of Promat d.o.o. Slovenia

Kopaonička 18

18000 Niš

T +381 18 4 530 297

M +381 64 61 39 763

F +381 18 4 230 570

E info.rs@promat-see.com

# Croatia, Bosnia and Herzegovina

Branch office of Promat d.o.o. Slovenia

Samoborska 91

10090 Zagreb

T +385 1 349 63 24

F +385 1 379 41 54

E info.hr@promat-see.com

www.promat-see.com

# Albania, Kosovo

www.promat-see.com

# Slovakia

Branch office of Promat d.o.o. Slovenia

Pražská 2

949 11 Nitra

T +421 377 729 165

E info.sk@promat-see.com www.promat-see.com

## Hungary

Branch office of Promat d.o.o. Slovenia

Pirosrózsa u. 32.

1163 Budapest

T +36 1 317 58 91

E info.hu@promat-see.com

www.promat-see.com

For all other Promat addresses, please visit www.promat-international.com.